



IZAMIN CA46

PRODUCT DESCRIPTION

Excellent water and corrosion resistance
Excellent adhesion
Excellent pigment and substrate wetting
Good chemical resistance
Long pot life and fast drying

STORAGE & SHELF LIFE

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C
Exposure to direct sunlight should be avoided. The shelf life of the resin under the mentioned storage conditions is 1 year.

APPLICATION

Maintenance and marine coatings
Tank and pipe coatings
Flooring compounds
Masonry and pool coatings
Adhesives

DELIVERY FORM

IBC - 1000 kg
Barrel - 200 kg
Bulk

MATERIAL SAFETY

SDS for this product is available on request

TECHNICAL SPECIFICATIONS

Property	Value	Unit	Test Method
Amine value	350-450	mg KOH/g	DIN 16954
Viscosity (Brookfield 25°C)	200-350	cP	DINEN ISO 3219/A-3
Colour	Max 2	Gardner	TS EN ISO 4630
Density (20 °C)	1,00-1,04	gr/cm3	TS EN ISO 2811-1
Amine hydrogen equiv. weight	Approx 93	gr/mol	-
Pot-life & Touch drying / min	20-30	fr.20->40°Cw.	DIN EN 22719
Flash point	>100	°C	-

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet