

## IZELCRYL 24T60

### PRODUCT DESCRIPTION

Air dried, polyacrylic and thermoplastic resin

### STORAGE & SHELF LIFE

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C Exposure to direct sunlight should be avoided. The shelf life of the resin under the mentioned storage conditions is 1 year.

### CHEMICAL COMPOSITION

1 component acrylic resin with toluene.

### DELIVERY

IBC - 1000 kg  
Barrel - 200 kg  
Bulk

### APPLICATION

Auto repair  
Industrial paints and varnishes  
Road marking  
Wood  
Floor paint

### MATERIAL SAFETY

SDS for this product is available on request

### CAN BE APPLIED OVER

Concrete surfaces  
Metal surfaces

### TECHNICAL SPECIFICATIONS

Property	Value	Unit	Test Method
Solvent type	Toluene	-	-
Solid content	59-61	%	TS EN ISO 3251
Viscosity (Brookfield 25 °C)	9850-14800	cP	TS 6126 EN ISO 2555
Acid value	Max 18	mg KOH/g	TS 2366 EN ISO 2114
Colour	Max 3	Gardner	TS EN ISO 4630
Density (20 °C)	0,99-1,03	gr/cm <sup>3</sup>	TS EN ISO 2811-1

### SOLUBILITY

White spirit	Insoluble
Acetone	Soluble
Toluene	Soluble
Xylene	Soluble

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet

IZEL KIMYA SAN. Ve TIC. A.Ş.

Gebkim V (Kimya) Organize Sanayi Bölgesi İbrahim Başaran Caddesi No. 9 Dilovası / KOCAELİ

Phone: +90 262 754 22 33 (pbx) Fax: +90 262 754 11 99

[www.izelkimya.com.tr](http://www.izelkimya.com.tr)

