

SYNTHETIC RESINS - PAINT AND VARNISH / Solvent Based

IZELCRYL 26X60 2,6 %OH

PRODUCT DESCRIPTION

IZELCRYL 26X60 2,6 %OH is a hydroxyl functional acrylic resin developed for The resin should be stored indoors in original, unopened, undamaged use in two component systems when cured with polyisocyanate.

Characteristics of IZELCRYL 26X60 2,6 %OH based coatings include: High gloss Excellent hardness Excellent weathering properties Excellent chemical resistance

Good application properties

MATERIAL SAFETY

SDS for this product is available on request

APPLICATION

Auto repair

Industrial paints and varnishes

Marine paints and varnishes

Wood

Furniture varnish

container in a dry place at storage temperature between 5-30 °C

STORAGE & SHELF LIFE

Exposure to direct sunlight should be avoided. The shelf life of the resin under the mentioned storage conditions is 1 year.

CHEMICAL COMPOSITION

DELIVERY FORM

The solvents chosen for paints and lacquers based on IZELCRYL 26X60 2,6 %OH should be free of water and should not contain groups that react with isocyanates.

TECHNICAL SPECIFICATIONS

IBC - 1000 kg Barrel - 200 kg

Bulk

Property	Value	Unit	Test Method
Solvent type	Xylene	-	-
Solid content	58-62	%	TS EN ISO 3251
Viscosity (Brookfield 25 °C)	1760-3620	сP	TS 6126 EN ISO 2555
Acid value	Max 13	mg KOH/g	TS 2366 EN ISO 2114
Colour	Max 1	Gardner	TS EN ISO 4630
Hydroxyl value (On solid)	approx.2,6	%	Izel Test Methods
Hydroxyl value (Supply form)	1,6±0,2	%	Izel Test Methods
Density (20 °C)	0,97-1,01	gr/cm ³	TS EN ISO 2811-1

The amount of polyisocyanate used to 100 g of acrylic resin (100% solid)

$$=\frac{42\times100\times OH~\%}{17\times NCO~\%}\times\frac{NCO}{OH}$$

General suggestion is NCO/OH ratio should be equal to 1. But;

If the product has to be harder and has more resistance for chemicals; NCO/OH>1

If the product has to be flexible has good adhesion and weatherability; NCO/OH<1

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet





TECHNICAL DATA SHEET

2 K ACRYLIC RESIN