



IZELKYD LO 63D60

PRODUCT DESCRIPTION

Solvent based, long oil and oxidative drying alkyd resin
Very good yellowing resistance
High colour durability and gloss retention
High humidity resistance

STORAGE & SHELF LIFE

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C. Exposure to direct sunlight should be avoided. The shelf life of the resin under the mentioned storage conditions is 1 year.

COMPATIBILITY

Long and medium alkyd resin Compatible
Hydroxyl acrylic resin Incompatible

DELIVERY FORM

IBC - 900 kg
Barrel - 185 kg
Bulk

APPLICATION

Parquet varnishes
Synthetic paints and varnishes
Wood
Construction paint

MATERIAL SAFETY

SDS for this product is available on request

TECHNICAL SPECIFICATIONS

Property	Value	Unit	Test Method
Modification	Specific	-	-
Type of oil	Sunflower fatty acid	-	-
Oil percentage	63	%	-
Solvent type	D40	-	-
Solid content	59-61	%	TS EN ISO 3251
Viscosity (Gardner 25 °C)	Y-Z1 / 26,8-39,6	Gardner/sec	ASTM D 1545-13
Acid value	Max 12	mg KOH/g	TS 2366 EN ISO 2114
Colour (%50 Solid)	Max 6	Gardner	TS EN ISO 4630
Density (20 °C)	0,95-0,98	gr/cm ³	TS EN ISO 2811-1

SOLUBILITY

Acetone Soluble
White spirit Soluble
Xylene Soluble
Toluene Soluble

RECOMMENDED DRYER RATES

Cobalt 0,05-0,07 %
Zirconium 0,2-0,4 %
Calcium 0,1-0,3 %
Recommended scatter rates over 100% solid alkyd metal percentages.

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet

IZEL KIMYA SAN. Ve TIC. A.Ş.

Gebkim V (Kimya) Organize Sanayi Bölgesi İbrahim Başaran Caddesi No. 9 Dilovası / KOCAELİ

Phone: +90 262 754 22 33 (pbx) Fax: +90 262 754 11 99

www.izelkimya.com.tr