



IZELKYD LO N 63X70

PRODUCT DESCRIPTION

Solvent based, long oil and oxidative drying alkyd resin
High colour durability and gloss retention
Very good yellowing resistance

STORAGE & SHELF LIFE

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C. Exposure to direct sunlight should be avoided. The shelf life of the resin under the mentioned storage conditions is 1 year.

COMPATIBILITY

Long oil alkyd resin	Compatible
Cellulose nitrate	Compatible
Short oil alkyd resin	Incompatible
Amino resins	Compatible

DELIVERY FORM

IBC - 1000 kg
Barrel - 200 kg
Bulk

APPLICATION

Parquet varnishes
Synthetic paints and varnishes
Wood
Construction paint

MATERIAL SAFETY

SDS for this product is available on request

TECHNICAL SPECIFICATIONS

Property	Value	Unit	Test Method
Modification	Specific	-	-
Type of oil	Sunflower fatty acid	-	-
Oil percentage	63	%	-
Solvent type	Xylene	-	-
Solid content	69-71	%	TS EN ISO 3251
Viscosity (Gardner 25 °C)	S-V / 7,3-13	Gardner/sec	ASTM D 1545-13
Viscosity (60%, Gardner 25 °C)	F-H / 2,05-2,93	Gardner/sec	ASTM D 1545-13
Acid value	Max 11	mg KOH/g	TS 2366 EN ISO 2114
Colour (%50 Solid)	Max 7	Gardner	TS EN ISO 4630

SOLUBILITY

Acetone	Soluble
White spirit	Soluble
Xylene	Soluble
Toluene	Soluble

RECOMMENDED DRYER RATES

Cobalt	0,05-0,07 %
Zirconium	0,2-0,4 %
Calcium	0,1-0,3 %

Recommended scatter rates over 100% solid alkyd metal percentages.

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet