



SYNTHETIC RESINS - PAINT AND VARNISH / Solvent Based

MEDIUM OIL ALKYD RESIN

IZELKYD MO 50X60

PRODUCT DESCRIPTION

Solvent based, medium oil and oxidative drying alkyd resin
High yellowing resistance
High colour durability and gloss retention
High humidity resistance

COMPATIBILITY

Long oil alkyd resins Incompatible
Short oil alkyd resins Compatible

APPLICATION

Auto repair
Industrial paints and varnishes
Road marking
Synthetic paints and varnishes
Wood
Construction paint

STORAGE & SHELF LIFE

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C. Exposure to direct sunlight should be avoided. The shelf life of the resin under the mentioned storage conditions is 1 year.

DELIVERY FORM

IBC - 1000 kg
Barrel - 200 kg
Bulk

MATERIAL SAFETY

SDS for this product is available on request

TECHNICAL SPECIFICATIONS

Property	Value	Unit	Test Method
Modification	TDI	-	-
Type of oil	Soybean oil	-	-
Oil percentage	50	%	-
Solvent type	Xylene	-	-
Solid content	59-61	%	TS EN ISO 3251
Viscosity (Gardner 25 °C)	Z2-Z3 / 53,1-67,9	Gardner/sec	ASTM D 1545-13
Acid value	Max 11	mg KOH/g	TS 2366 EN ISO 2114
Density (20 °C)	0,98-1,01	gr/cm ³	TS EN ISO 2811-1
Colour (%50 Solid)	Max 6	Gardner	TS EN ISO 4630

SOLUBILITY

White spirit Insoluble
Acetone Soluble
Toluene Soluble
Xylene Soluble

RECOMMENDED DRYER RATES

Cobalt 0,04-0,06 %
Zirconium 0,25-0,45 %
Calcium 0,15-0,35 %

Recommended scatter rates over 100% solid alkyd metal percentages.

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet

IZEL KIMYA SAN. Ve TIC. A.Ş.

Gebkim V (Kimya) Organize Sanayi Bölgesi İbrahim Başaran Caddesi No. 9 Dilovası / KOCAELİ

Phone: +90 262 754 22 33 (pbx) Fax: +90 262 754 11 99

www.izelkimya.com.tr