

**IZELKYD POL F O 28T60****PRODUCT DESCRIPTION**

Two component short oil alkyd for filling varnishes
Excellent for the 2K PU wood sanding sealer varnishes for NC lacquers, paint and varnishes
Excellent hardness and very high gloss film
Fast solvent release properties
Good resistance to outside factors

STORAGE & SHELF LIFE

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C. Exposure to direct sunlight should be avoided. The shelf life of the resin under the mentioned storage conditions is 1 year.

COMPATIBILITY

Long oil alkyd resins Incompatible
Short oil alkyd resins Compatible

DELIVERY FORM

IBC - 1000 kg
Barrel - 200 kg
Bulk

APPLICATION

Furniture NC
Furniture PU
Wood

MATERIAL SAFETY

SDS for this product is available on request

TECHNICAL SPECIFICATIONS

Property	Value	Unit	Test Method
Modification	Specific	-	-
Type of oil	Soybean oil	-	-
Oil percentage	28	%	-
Solvent type	Toluene	-	-
Solid content	59-61	%	TS EN ISO 3251
Viscosity (Gardner 25 °C, %55 Solid)	Z3-Z5 / 67,9-144,5	Gardner/sec	ASTM D 1545-13
Acid value	Max 11	mg KOH/g	TS 2366 EN ISO 2114
OH value	4,4	%	AT %100 SOLID (CALCULATED)
Density (20 °C)	1,02-1,05	gr/cm ³	TS EN ISO 2811-1
Colour (%50 Solid)	Max 7	Gardner	TS EN ISO 4630

SOLUBILITY

Acetone Soluble
White spirit Insoluble
Xylene Soluble
Toluene Soluble

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet

IZEL KIMYA SAN. Ve TIC. A.Ş.

Gebkim V (Kimya) Organize Sanayi Bölgesi İbrahim Başaran Caddesi No. 9 Dilovası / KOCAELİ

Phone: +90 262 754 22 33 (pbx) Fax: +90 262 754 11 99

www.izelkimya.com.tr