

**IZELPOL 10XM70****PRODUCT DESCRIPTION**

Oil free, hydroxyl-bearing saturated polyester  
Good compatibility with CAB

**STORAGE & SHELF LIFE**

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C. Exposure to direct sunlight should be avoided. The shelf life of the resin under the mentioned storage conditions is 1 year.

**APPLICATION**

Stoving coating  
Coil coating

**DELIVERY FORM**

IBC - 1000 kg  
Barrel - 200 kg  
Bulk

**CAN BE APPLIED OVER**

Can coating and coil top coating applications for exterior

**MATERIAL SAFETY**

SDS for this product is available on request

**TECHNICAL SPECIFICATIONS**

Property	Value	Unit	Test Method
Solvent Type	Xylene/Methoxy propanol	-	-
Solid content	68-72	%	TS EN ISO 3251
Viscosity (Brookfield 25°C)	1800-2500	cP	TS 6126 EN ISO 2555
Acid value	Max 8	mg KOH/g	TS 2366 EN ISO 2114
Colour	Max 3	Gardner	TS EN ISO 4630
Hydroxyl value	25-40	mg KOH/g	IZEL KİMYA TEST METHODU
Molecular weight	8200-10000	gr/mol	IZEL KİMYA TEST METHODU
Tg	17-20	°C	ASTM D 7028-7
Density (20 °C)	1,00-1,04	gr/cm <sup>3</sup>	TS EN ISO 2811-1

**SOLUBILITY**

White Spirit	Insoluble
Terebentine	Insoluble
Xylene	Soluble
Toluene	Soluble
Acetone	Soluble

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet

IZEL KİMYA SAN. VE TİC. A.Ş.

Gebkim V (Kimya) Organize Sanayi Bölgesi İbrahim Başaran Caddesi No. 9 Dilovası / KOCAELİ

Phone: +90 262 754 22 33 (pbx) Fax: +90 262 754 11 99

[www.izelkimya.com.tr](http://www.izelkimya.com.tr)