

**IZELPOL 19NB66****PRODUCT DESCRIPTION**

Oil free, hydroxyl-bearing saturated polyester  
Good compatibility with CAB

**STORAGE & SHELF LIFE**

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C. Exposure to direct sunlight should be avoided. The shelf life of the resin under the mentioned storage conditions is 1 year.

**APPLICATION**

Coil coating primer  
Stoving coating  
Can coating

**DELIVERY FORM**

IBC - 1000 kg  
Barrel - 200 kg  
Bulk

**CAN BE APPLIED OVER**

Exterior can coating and coil top coating applications for primer coat

**MATERIAL SAFETY**

SDS for this product is available on request

**TECHNICAL SPECIFICATIONS**

Property	Value	Unit	Test Method
Solvent Type	Solvent Naphta/Butyl Glycol	-	-
Solid content	64-68	%	TS EN ISO 3251
Viscosity (Brookfield 23°C)	900-1500	cP	TS 6126 EN ISO 2555
Acid value	Max 6	mg KOH/g	TS 2366 EN ISO 2114
Colour	Max 2	Gardner	TS EN ISO 4630
Hydroxyl value	50-70	mg KOH/g	IZEL KİMYA TEST METHODU
Molecular weight	4000-6500	gr/mol	IZEL KİMYA TEST METHODU
Density (20 °C)	1,085-1,115	gr/cm <sup>3</sup>	TS EN ISO 2811-1

**SOLUBILITY**

Acetone Soluble

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet

IZEL KİMYA SAN. Ve TİC. A.Ş.

Gebkim V (Kimya) Organize Sanayi Bölgesi İbrahim Başaran Caddesi No. 9 Dilovası / KOCAELİ

Phone: +90 262 754 22 33 (pbx) Fax: +90 262 754 11 99

[www.izelkimya.com.tr](http://www.izelkimya.com.tr)