

**IZELKYD URAL 56D60****PRODUCT DESCRIPTION**

TDI modified solvent based oxidative drying alkyd resin  
High yellowing resistance  
High colour durability and gloss retention

**STORAGE & SHELF LIFE**

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C. Exposure to direct sunlight should be avoided. The shelf life of the resin under the mentioned storage conditions is 1 year.

**APPLICATION**

Parquet varnishes  
Marine paints and varnishes  
Wood  
Anti corrosive paint  
Industrial paints and varnishes  
Stoving enamels

**DELIVERY FORM**

IBC - 1000 kg  
Barrel - 200 kg  
Bulk

**MATERIAL SAFETY**

SDS for this product is available on request.

**TECHNICAL SPECIFICATIONS**

Property	Value	Unit	Test Method
Modification	TDI	-	-
Type of oil	Soybean oil	-	-
Oil percentage	56	%	-
Solvent type	D40	-	-
Solid content	59-61	%	TS EN ISO 3251
Viscosity (Gardner 25 °C )	Z-Z2 / 33,3-53,1	Gardner/sec	ASTM D 1545-13
Acid value	Max 4	mg KOH/g	TS 2366 EN ISO 2114
Colour (%50 Solid)	Max 6	Gardner	TS EN ISO 4630

**SOLUBILITY**

Acetone Soluble  
White spirit Soluble  
Terebentine Soluble

**RECOMMENDED DRYER RATES**

Cobalt 0,04-0,06 %  
Zirconium 0,25-0,45 %  
Calcium 0,15-0,35 %

Recommended scatter rates over 100% solid alkyd metal percentages.

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet

IZEL KIMYA SAN. Ve TIC. A.Ş.

Gebkim V (Kimya) Organize Sanayi Bölgesi İbrahim Başaran Caddesi No. 9 Dilovası / KOCAELİ

Phone: +90 262 754 22 33 (pbx) Fax: +90 262 754 11 99

[www.izelkimya.com.tr](http://www.izelkimya.com.tr)